

BAB 5

KESIMPULAN DAN SARAN

5.1. Kesimpulan

1. Partikel kalsium karbonat dengan larutan pati berhasil disintesa dengan morfologi bola (vaterite).
2. Morfologi bola juga berhasil disintesa pada komposisi perbandingan surfaktan PF127:FC-4 = 1:3.
3. Profil pelepasan kurkumin dari partikel CaCO_3 memenuhi persamaan model 1st order yang menyatakan pori yang homogen pada partikel CaCO_3 .

5.2. Saran

1. Perlu adanya analisa N2 sorption dan XRD untuk karakterisasi lebih lanjut.

DAFTAR PUSTAKA

- [1] S. Jambhrunkar, S. Karmakar, and A. Popat, “Mesoporous silica nanoparticles enhance cytotoxicity of curcumin,” *R. Soc. Chem.*, vol. 4, pp. 709–712, 2014.
- [2] S. B. Hartono, L. Hadisoewignyo, W. Irawaty, L. Trisna, and R. Wijaya, “Porous silica nanoparticles as carrier for curcumin delivery,” *AIP Conf. Proc.*, vol. 1945, 2018.
- [3] N. Hao, K. W. Jayawardana, X. Chen, and M. Yan, “One-step synthesis of amine-functionalized hollow mesoporous silica nanoparticles as efficient antibacterial and anticancer materials,” *ACS Appl. Mater. Interfaces*, vol. 7, no. 2, pp. 1040–1045, 2015.
- [4] P. K J, “Multi-Functional Silver Nanoparticles for Drug Delivery: A Review,” *Int. J. Curr. Res. Rev.*, vol. 9, no. May, pp. 1–5, 2017.
- [5] A. Mukherjee, I. Mohammed Sadiq, T. C. Prathna, and N. Chandrasekaran, “Antimicrobial activity of aluminium oxide nanoparticles for potential clinical applications,” *Sci. against Microb. Pathog. Commun. Curr. Res. Technol. Adv.*, pp. 245–251, 2011.
- [6] F. Lotfipour, S. Maleki Dizaj, and M. Barzegar - Jalali, “Calcium Carbonate Nanoparticles ; Potential in Bone and Tooth Disorders,” *Pharm. Sci.*, vol. 20, no. March, pp. 175–182, 2015.
- [7] R. Salomão, L. M. M. Costa, and G. M. de Olyveira, “Precipitated Calcium Carbonate Nano-Microparticles: Applications in Drug Delivery,” *Adv. Tissue Eng. Regen. Med. Open Access*, vol. 3, no. 2, pp. 336–340, 2017.
- [8] S. Maleki Dizaj, M. Barzegar-Jalali, M. H. Zarrintan, K. Adibkia, and F. Lotfipour, “Calcium carbonate nanoparticles as cancer drug delivery system,” *Expert Opin. Drug Deliv.*, vol. 12, no. 10, pp. 1649–1660, 2015.
- [9] T. Huang, M. W. Ma, and H. Newmark, “Inhibitory effects of dietary curcumin on forestomach, duodenal, and colon carcinogenesis in mice,” *Cancer Res.*, vol. 54, no. 22, pp. 1–7, 1994.
- [10] E. Meiyanto, “Kurkumin sebagai obat kanker: menelusuri mekanisme aksinya,” *Maj. Farm. Indones.*, vol. 10, pp. 224–236, 1999.
- [11] R. Wilken, M. S. Veena, M. B. Wang, and E. S. Srivatsan, “Curcumin: A review of anti-cancer properties and therapeutic activity in head and neck squamous cell carcinoma,” *Mol. Cancer*, vol. 10, pp. 1–19, 2011.
- [12] H. Heydari Sheikh Hossein, A. Zarrabi, and A. Zarepour, “Design and construction of curcumin - loaded targeted iron oxide nanoparticles for cancer treatment,” *J. Babol Univ. Med. Sci.*, vol. 19, no. 6, pp. 64–70, 2017.
- [13] S. Bannerjee *et al.*, “Drug delivery systems: An updated review,” *Int. J.*

- Pharm. Investig.*, vol. 2, no. 1, p. 2, 2012.
- [14] N. Sahoo, A. Abbas, and C. Li, “Micro/Nanoparticle Design and Fabrication for Pharmaceutical Drug Preparation and Delivery Applications,” *Curr. Drug ther.*, vol. 3, no. 2, pp. 78–97, 2008.
 - [15] X. RONG, M. YANG, Q. HUANG, and P. ZHAO, “Controllable Synthesis of Calcium Carbonate with Different Morphologies and Phases Assisted by F127,” *ASIAN J. Chem.*, vol. 26, pp. 3971–3976, 2014.
 - [16] W. Wei, G. Hu, D. Yu, T. Mcleish, Z. Su, and Z. Shen, “Preparation of Hierarchical Hollow CaCO₃ Particles and the Application as,” pp. 15808–15810, 2010.
 - [17] Y. B. Yu, “Fluorocarbon nanoparticles as multifunctional drug delivery vehicles,” *J. Drug Target.*, vol. 14, no. 10, pp. 663–669, 2006.
 - [18] J. Liu, S. B. Hartono, A. Popat, S. Z. Qiao, G. Qing (Max) Lu, and F. Stahr, “Mesoporous silica nanoparticles for bioadsorption, enzyme immobilisation, and delivery carriers,” *Nanoscale*, vol. 3, no. 7, p. 2801, 2011.
 - [19] W. Ge *et al.*, “Enhancing the oral bioavailability of biochanin A by encapsulation in mixed micelles containing Pluronic F127 and Plasdone S630,” *Int. J. Nanomedicine*, vol. Volume 12, pp. 1475–1483, 2017.
 - [20] J. J. Escobar-Chávez, M. López-Cervantes, A. Naik, Y. N. Kalia, D. Quintanar-Guerrero, and A. Ganem-Quintanar, “Applications of thermo-reversible pluronic F-127 gels in pharmaceutical formulations,” *J. Pharm. Pharm. Sci.*, vol. 9, no. 3, pp. 339–358, 2006.
 - [21] Y. Zhang, F. Yu, W. Cheng, J. Wang, and J. Ma, “Adsorption Equilibrium and Kinetics of the Removal of Ammoniacal Nitrogen by Zeolite X/Activated Carbon Composite Synthesized from Elutritilite,” *J. Chem.*, vol. 2017, pp. 1–9, 2017.
 - [22] S. L. Yefimova *et al.*, “Synthesis and characterization of mesoporous CaCO₃@PSS microspheres as a depot system for sustained Methylene Blue delivering,” *Microporous Mesoporous Mater.*, vol. 236, pp. 120–128, 2016.
 - [23] Q. Zhao, B. Han, Z. Wang, C. Gao, C. Peng, and J. Shen, “Hollow chitosan-alginate multilayer microcapsules as drug delivery vehicle: doxorubicin loading and in vitro and in vivo studies,” *Nanomedicine Nanotechnology, Biol. Med.*, vol. 3, no. 1, pp. 63–74, 2007.
 - [24] C. Peng, Q. Zhao, and C. Gao, “Sustained delivery of doxorubicin by porous CaCO₃ and chitosan/alginate multilayers-coated CaCO₃ microparticles,” *Colloids Surfaces A Physicochem. Eng. Asp.*, vol. 353, no. 2–3, pp. 132–139, 2010.
 - [25] C. He, B. Ren, C. Wang, X. Liu, F. Zeng, and Z. Tong, “Combination of adsorption by porous CaCO₃ microparticles and encapsulation by

- polyelectrolyte multilayer films for sustained drug delivery," *Int. J. Pharm.*, vol. 308, no. 1–2, pp. 160–167, 2005.
- [26] B. Kanoje, J. Parikh, and K. Kuperkar, "Crystallization study and morphology behaviour of calcium carbonate crystals in aqueous Surfactant-Pluronics® prototype," *J. Mater. Res. Technol.*, no. x x, pp. 1–7, 2018.
 - [27] Y. Xiang, J. Han, G. Zhang, F. Zhan, D. Cai, and Z. Wu, "Efficient Synthesis of Starch-Regulated Porous Calcium Carbonate Microspheres as a Carrier for Slow-Release Herbicide," *ACS Sustain. Chem. Eng.*, vol. 6, no. 3, pp. 3649–3658, 2018.
 - [28] S. B. Hartono, L. Hadisoewignyo, Y. Yang, A. K. Meka, Antaresti, and C. Yu, "Amine functionalized cubic mesoporous silica nanoparticles as an oral delivery system for curcumin bioavailability enhancement," *Nanotechnology*, vol. 27, no. 50, pp. 1–7, 2016.
 - [29] P. N. M. DASH SUVAKANTA, N. LILAKANTA, and P. CHOWDHURY, "218 SUVAKANTA DASH et al," *Acta Pol. Pharm. ñ Drug Res.*, vol. 67, no. 3, pp. 217–223, 2010.
 - [30] G. Singhvi and R. Singh, "In-vitro drug release characterization models," *Int. J. Pharm. Stud. Res.*, vol. II, no. I, 2011.