

## CHAPTER V

### CONCLUSION AND RECOMMENDATION

#### V.1. Conclusion

Synthesize of bentonite-alginate polymer nanocomposite was successfull, which can be seen from the characterization of composite before and after modification, which was marked with the present of some of peaks wavelength shifted for sodium alginate into bentonite-alginate composite.

From effect of pH, adsorbent has higher pH solution than  $pH_{pzc}$ , it determines adsorbent has excess  $\text{OH}^-$ . Therefore, it can adsorpt the cationic dye with negatively charged sites.

The removal of crystal violet dye using bentonite-alginate composite in kinetic adsorption was succesfull using Pseudo-second order equation, which is proven from the good value of correlation factor ( $R^2$ ), higher than 0.9883. Pseudo-second order determines chemisorption processes as rate limiting step.

It was found that Freundlich isotherm equation gave the best representation for adsorption equilibrium data of crystal violet removal using bentonite-alginate nanocomposite, shown by the consistency of parameter value of Freundlich equation. The increasing of mass ratio in composite making, adsorption capacity of composite also increases. The temperature has significant effect of adsorption. The adsorption capacity of composite is increasing along the temperature increases.

#### V.2. Recommendation

Modification of bentonite-alginate polymer nanocomposite as adsorbent is recommended in order to increase the ability of adsorption cationic dye.

## REFERENCES

- AHMAD, R. A. M., ANAM 2015. *Sequestration of Heavy Metal Ions by Methionine Modified Bentonite/Alginate (Meth-Bent/Alg): A Bionanocomposite. Groundwater for Sustainable Development*, Vol. 1, 50-58.
- A.AKBARI, REMIGLY, J. C. & APTEL, P. 2002. *Treatment of textile dye effluent using a polyamide-based nanofiltration membrane. Chemical Engineering and Processing*, Vol. 41, 601-609.
- AKINOLA, L. & UMAR, A. 2015. *Adsorption of Crystal Violet onto Adsorbents Derived from Agricultural Wastes: Kinetic and Equilibrium Studies. Journal Application Science Environment*, Vol. 19(2), 279-288.
- AL-BASTAKI, N. 2004. *Removal of methyl orange dye and Na<sub>2</sub>SO<sub>4</sub> salt from synthetic waste water using reverse osmosis. Chemical Engineering and Processing*, Vol. 43, 1561-1567.
- AL-FUTAISI, A., JAMRAH, A. & AL-HANAI, R. 2007. *Aspects of cationic dye molecule adsorption to palygorskite. Desalination*, Vol. 214, 327-342.
- ALI, K., DE, P., BHOWMILK, G. C. & DAS, N. 2016. *Adsorption behavior of methylene blue onto gellan gum-bentonite composite beads for bioremediation application. World Journal of Pharmaceutical Sciences*, Vol. 4(1), 68-72.
- ARSLAN, I., BALCIOGLU, I. A. & BAHNEMANN, D. W. 2000. *Advanced chemical oxidation of reactive dyes in simulated dyehouse effluents by ferrioxalate-Fenton/UV-A and TiO<sub>2</sub>/UV-A processes. Dyes and Pigments*, Vol. 47, 207-218.
- BANAT, I. M., NIGAM, P., SINGH, D. & MARCHANT, R. 1996. *Microbial decolorization of textile-dye-containing effluents: A review. Bioresource Technology*, Vol. 58, 217-227.
- BANERJEE, S. & CHATTOPADHYAYA, M. C. 2013. *Adsorption characteristics for the removal of a toxic dye, tetrazine from aqueous from aqueous solutions by a low cost agricultural by-product. Arabian Journal of Chemistry*.
- BENHOURIA, A., ISLAM, M. A., ZAGHOUANE-BOUDIAF, H., BOUTAHALA, M. & HAMEED, B. H. 2015. *Calcium alginate-bentonite-activated carbon composite beads as highly effective adsorbent for methylene blue. Chemical Engineering Journal*, Vol. 270, 621-630.

- BHATTACHARYYA, R. & RAY, S. K. 2014. *Micro- and nano-sized bentonite filled composite superabsorbents of chitosan and acrylic copolymer for removal of synthetic dyes from water. Applied Clay Science.*
- CHAKRABORTY, S., DE, S., DASGUPTA, S. & BASU, J. K. 2005. *Adsorption study for the removal of basic dye: experimental and modeling. Chemosphere*, Vol. 58, 1079-1086.
- DONAT, R., ESEN, K., CETISLI, H. & AYTAS, S. 2009. *Adsorption of uranium(VI) onto Ulva sp.-sepiolite composite. Journal of Radioanalytical and Nuclear Chemistry*, Vol. 279(1), 253-261.
- ELY, A., BAUDU, M. & KANKOU, M. O. S. A. O. 2011. *Copper and nitrophenol removal by low cost alginate/Mauritanian clay. Chemical Engineering Journal*, Vol. 178, 168-174.
- EREN, E. & AFSIN, B. 2008. *Investigation of a basic dye adsorption from aqueous solution onto raw and pre-treated bentonite surfaces. Dyes and Pigments*, Vol. 76, 220-225.
- FERRIN, P., KANDOI, S., NILEKAR, A. U. & MAVRIKAKIS, M. 2012. *Hydrogen adsorption, absorption and diffusion on and in transition metal surfaces: A DFT study. Surface Science*, Vol. 606, 679-689.
- GARG, V. K., GUPTA, R., YADAV, A. B. & KUMAR, R. 2003. *Dye removal from aqueous solution by adsorption on treated sawdust. Bioresource Technology*, Vol. 89, 121-124.
- GHANBARI, K. 2014. *Fabrication of silver nanoparticles-polypyrrole composite modified electrode for electrocatalytic oxidation of hydrazine. Synthetic Metals*, Vol. 195, 234-240.
- HASSAN, A. F., ABDEL-MOHSEN, A. M. & FOUDA, M. M. G. 2014. *Comparative study of calcium alginate, activated carbon, and their composite beads on methylene blue adsorption. Carbohydrate Polymers*, Vol. 102, 192-198.
- ISMADJI, S. 2015. *Clay Materials for Environmental Remediation.*
- JAWAD, E. D., KHUDHAIR, S. H. & N., H. A. 2011. *A Thermodynamic Study of Adsorption of Some Dyes on Iraqi Bentonite Modified Clay. European Journal of Scientific Research*, Vol. 60, 63-70.
- JR., O. P., CAZETTA, A. L., SOUZA, I. A. F., BEDIN, K. C. & MARTINS, A. C. 2014. *Adsorption studies of methylene blue onto ZnCl<sub>2</sub>-activated carbon produced from buriti shells (*Mauritia flexuosa L.*). Journal of Industrial and Engineering Chemistry*, 1-7.
- JR., R. W. M., BAILLOD, C. R. & MIHELCIC, J. R. 2005. *Low-temperature inhibition of the activated sludge process by an industrial discharge containing the azo dye acid black 1. Water Research*, Vol. 39, 17-28.

- KARNLAND, O., OLSSON, S. & NILSSON, U. 2006. *Mineralogy and sealing properties of various bentonites and smectite-rich clay materials.*
- KOSWOJO, R., UTOMO, R. P., JU, Y.-H., AYUCITRA, A., SOETAREDJO, F. E., SUNARSO, J. & ISMADJI, S. 2010. *Acid Green 25 removal from wastewater by organo-bentonite from Pacitan.* *Applied Clay Science*, Vol. 48, 81-86.
- KURNIAWAN, A., SUTIONO, H., INDRASWATI, N. & ISMADJI, S. 2012. Removal of basic dyes in binary system by adsorption using rasasaponin-bentonite: Revisited of extended Langmuir model. *Chemical Engineering Journal*, Vol. 189-190, 264-274.
- LEE, C.-K., LIU, S.-S., JUANG, L.-C., WANG, C.-C., LIN, K.-S. & LYU, M.-D. 2007. *Application of MCM-41 for dyes removal from wastewater.* *Journal of Hazardous Materials*, Vol. 147, 997-1005.
- LI, L., WANG, S. & ZHU, Z. 2006. *Geopolymeric adsorbents from fly ash for dye removal from aqueous solution.* *Journal of Colloid and Interface Science*, Vol. 300, 52-59.
- MOUSSAVI, G. & MAHMOUDI, M. 2009. *Removal of azo and anthraquinone reactive dyes from industrial wastewaters using MgO nanoparticles.* *Journal of Hazardous Materials*, Vol. 168, 806-812.
- NGAH, W. S. W., TEONG, L. C. & HANAFIAH, M. A. K. M. 2011. *Adsorption of dyes and heavy metal ions by chitosan composites: A review.* *Carbohydrate Polymers*, Vol. 83, 1446-1456.
- OLADIPO, A. A. & GAZI, M. 2014. *Enhanced removal of crystal violet by low cost alginate/acid activated bentonite composite beads: Optimization and modelling using non-linear regression technique.* *Journal of Water Process Engineering*, 1-10.
- OTERO, M., ROZADA, F., CALVO, L. F., GARCIA, A. I. & MORAN, A. 2003. *Elimination of organic water pollutants using adsorbents obtained from sewage sludge.* *Dyes and Pigments*, Vol. 57, 55-65.
- PATIL, J. S., KAMALAPUR, M. V., MARAPUR, S. C. & KADAM, D. V. 2010. *Ionotropic Gelation and Polyelectrolyte Complexation: The Novel Technique to Design Hydrogel Particulate Sustained, Modulated Drug Delivery System: A Review.* *Nanomaterials and Biostructures*, Vol. 5(1), 241-248.
- PLAZINKI, W., RUDZINSKI, W. & PLAZINSKA, A. 2009. *Theoretical models of sorption kinetics including a surface reaction mechanism: A review.* *Advances in Colloid and Interface Science*, Vol. 152, 2-13.
- POPURI, S. R., VIJAYA, Y., BODDU, V. M. & ABBURI, K. 2009. *Adsorptive removal of copper and nickel ions from water using*

- chitosan coated PVC beads.* *Bioresource Technology*, Vol. 100, 194-199.
- PORKODI, K. & KUMAR, K. V. 2007. *Equilibrium, kinetics and mechanism modeling and simulation of basic and acid dyes sorption onto jute fiber carbon: Eosin yellow, malachite green and crystal violet single component systems.* *Journal of Hazardous Materials*, Vol. 143, 311-327.
- PUTRA, E. K., PRANOWO, R., SUNARSO, J., INDRASWATI, N. & ISMADJI, S. 2009. *Performance of activated carbon and bentonite for adsorption of amoxicillin from wastewater: Mechanisms, isotherms and kinetics.* *Water Research*, Vol. 43, 2419-2430.
- RAFATULLAH, M., SULAIMAN, O., HASHIM, R. & AHMAD, A. 2010. *Adsorption of methylene blue on low-cost adsorbents: A Review.* Vol. 177, 70-80.
- RAHARDJO, A. K., SUSANTO, M. J. J., KURNIAWAN, A., INDRASWATI, N. & ISMADJI, S. 2011. *Modified Ponorogo bentonite for the removal of ampicillin from wastewater.* *Journal of Hazardous Materials*, Vol. 190, 1001-1008.
- ROBINSON, T., MCMULLAN, G., MARCHANT, R. & NIGAM, P. 2001. *Remediation of dyes in textile effluent: a critical review on current treatment technologies with a proposed alternative.* *Bioresource Technology*, Vol. 77, 247-255.
- S.RAGHU & BASHA, C. A. 2007. *Chemical or electrochemical techniques, followed by ion exchange, for recycle of textile dye wastewater.* *Journal of Hazardous Materials*, Vol. 149, 324-330.
- SANDY, MARAMIS, V., KURNIAWAN, A., AYUCITRA, A., SUNARSO, J. & ISMADJI, S. 2012. *Removal of copper ions from aqueous solution by adsorption using LABORATORIES-modified bentonite (organo-bentonite).* *Chemical Science Engineering*, Vol. 6(1), 58-66.
- SHAYESTEH, H., RABAR-KELISHAMI, A. & NOROUZBEIGI, R. 2015. *Adsorption of malachite green and crystal violet cationic dyes from aqueous solution using pumice stone as a low-cost adsorbent: kinetic, equilibrium, and thermodynamic studies.* *Desalination and Water Treatment*, 1-10.
- SHENTILKUMAAR, S., KALAAMANI, P. & SUBBURAAM, C. V. 2006. *Liquid phase adsorption of Crystal violet onto activated carbons derived from male flowers of coconut tree.* *Journal of Hazardous Materials*, Vol. B136, 800-808.
- SHI, B., LI, G., WANG, D., FENG, C. & TANG, H. 2007. *Removal of direct dyes by coagulation: The performance of preformed polymeric*

- aluminum species. *Journal of Hazardous Materials*, Vol. 143, 567-574.
- TAN, W. S. & TING, A. S. Y. 2014. *Alginate-immobilized bentonite clay: Adsorption efficacy and reusability for Cu(II) removal from aqueous solution*. *Bioresource Technology*, Vol. 160, 115-118.
- WANG, C., YEDILER, A., LIENERT, D., WANG, Z. & KETTRUP, A. 2003. Ozonation of an azo dye C.I. Remazol Black 5 and toxicological assessment of its oxidation products. *Chemosphere*, Vol. 52, 1225-1232.
- ZHOU, C.-H., ZHANG, D., TONG, D.-S., WU, L.-M., YU, W.-H. & ISMADJI, S. 2012. Paper-like composites of cellulose acetate-organomontmorillonite for removal of hazardous anionic dye in water. *Chemical Engineering Journal*, Vol. 209, 223-234.